

### PRODUCT SPECIFICATION

Binder	Polyurethane
Colour	Natural
Cork Granule Size	0,5/2 mm

TEST METHOD	PROPERTY	UNIT	VALUE
ISO 7322	Specific weight	kg/m <sup>3</sup>	530-630
ISO 7322	Tensile strength	kPa	≥1200
ISO 7322	Compression	%	5-15
ISO 7322	Recovery	%	≥70
ISO 7322	Boiling water	-	No disaggregation

### Dimensional Tolerances

	Nominal Value (mm)	Tolerance (%)
Thickness	≥ 6 < 10	± 5%
Width/Length		± 1%

### GENERAL INFORMATION

We recommend storing the product at these conditions: 20° ± 3°C/60 ± 5% HR